

Translated English of Chinese Standard: GB21341-2022

www.ChineseStandard.net → Buy True-PDF → Auto-delivery.

Sales@ChineseStandard.net

GB

NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA

ICS 27.010

CCS F 01

GB 21341-2022

Replacing GB 21341-2017

**The Norm of Energy Consumption per Unit Production of
Ferroalloy**

铁合金单位产品能源消耗限额

Issued on: December 29, 2022

Implemented on: January 1, 2024

Issued by: State Administration for Market Regulation;

Standardization Administration of the People's Republic of China.

Table of Contents

Foreword	3
1 Scope	4
2 Normative References	4
3 Terms and Definitions	5
4 Levels of the Norm of Energy Consumption	5
5 Technical Requirements	7
6 Statistical Scopes and Calculation Methods	7
Appendix A (informative) Standard Coal Conversion Reference Coefficients of Various Energy Sources	10
Appendix B (normative) Table of Benchmark Composition of Ferroalloy Products ..	11

The Norm of Energy Consumption per Unit Production of Ferroalloy

1 Scope

This document specifies the levels, technical requirements, statistical scopes and calculation methods for the norm of energy consumption per unit product of ferroalloy (hereinafter referred to as energy consumption).

This document is applicable to the calculation and assessment of energy consumption per unit product of 9 varieties: ferrosilicon produced by ferroalloy submerged arc furnaces, high carbon ferromanganese produced by electric furnaces (limited to high carbon ferromanganese produced through the flux-free smelting process), manganese-silicon alloy, low carbon ferromanganese-silicon, high carbon ferrochromium and charge ferrochromium, and micro-carbon ferromanganese and medium (low) carbon ferrochromium produced by electric ferroalloy refining furnaces, and blast furnace ferromanganese produced by ferroalloy blast furnace, as well as the energy consumption control of new construction, renovation and extension projects.

2 Normative References

The contents of the following documents constitute indispensable clauses of this document through the normative references in the text. In terms of references with a specified date, only versions with a specified date are applicable to this document. In terms of references without a specified date, the latest version (including all the modifications) is applicable to this document.

GB/T 2272 Ferrosilicon

GB/T 2589 General Rules for Calculation of the Comprehensive Energy Consumption

GB/T 3795 Ferromanganese

GB/T 4008 Ferromanganese-silicon

GB/T 5683 Ferrochromium

GB/T 12723 General Principles of Stipulation of Energy Consumption Norm for Unit Product

GB/T 14984.1 Ferroalloys - Vocabulary - Part 1: Materials

3 Terms and Definitions

The terms and definitions defined in GB/T 12723, and the following terms and definitions are applicable to this document.

3.1 comprehensive energy consumption per unit product of ferroalloy

Comprehensive energy consumption per unit product of ferroalloy refers to the amount of various energy sources consumed by ferroalloy enterprises to produce 1 benchmark ton (converted in accordance with the benchmark composition of the main elements) of qualified ferroalloy products during the reporting period.

3.2 smelting electricity consumption per unit product of ferroalloy

Smelting electricity consumption per unit product of ferroalloy refers to the electricity consumption in the smelting process by ferroalloy enterprises to produce 1 benchmark ton (converted in accordance with the benchmark composition of the main elements) of qualified ferroalloy products during the reporting period.

3.3 coke consumption per unit product of ferroalloy

Coke consumption per unit product of ferroalloy refers to the amount of coke (dry tons) consumed by ferroalloy blast furnace production enterprises to produce 1 benchmark ton (converted in accordance with the benchmark composition of the main elements) of qualified ferroalloy products during the reporting period.

3.4 low carbon ferromanganese-silicon

Low carbon ferromanganese-silicon refers to ferromanganese-silicon whose carbon content is not greater than 0.3%.

3.5 charge ferrochromium

Charge ferrochromium refers to ferrochromium whose chromium content is 45% ~ 52% and carbon content is below 10%.

4 Levels of the Norm of Energy Consumption

The indicators of the norm of energy consumption per unit product of ferroalloy production enterprises include smelting electricity consumption per unit product of ferroalloy, coke consumption per unit product of ferroalloy and comprehensive energy consumption per unit product of ferroalloy. The levels of the norm of energy consumption are shown in Table 1 and Table 2, in which, Level-1 represents the lowest energy consumption.

5 Technical Requirements

5.1 Limit Values of Energy Consumption per Unit Product of Existing Ferroalloy Production Enterprises

The indicators of the limit values of energy consumption per unit product of existing ferroalloy production enterprises include smelting electricity consumption per unit product, coke consumption per unit product and comprehensive energy consumption per unit product. The limit values shall be not greater than the Level-3 energy consumption indicators in Table 1 and Table 2.

5.2 Access Values of Energy Consumption per Unit Product of Newly Constructed, Reconstructed and Extended Ferroalloy Production Enterprises

The indicators of the access values of energy consumption per unit product of newly constructed, reconstructed and extended ferroalloy production enterprises include smelting electricity consumption per unit product, coke consumption per unit product and comprehensive energy consumption per unit product. The limit values shall be not greater than the Level-2 energy consumption indicators in Table 1 and Table 2.

6 Statistical Scopes and Calculation Methods

6.1 Statistical Scope and Valuing Principle of Energy Conversion Coefficient

6.1.1 Statistical scope

6.1.1.1 Statistical scope of comprehensive energy consumption per unit product of ferroalloy

The comprehensive energy consumption of electric furnace ferroalloy production enterprises shall include the smelting electrical energy consumption for heating the charge and maintaining normal furnace conditions; power energy consumption in the production and processing process (including raw material preparation, transportation, alloy pouring, finishing, material and alloy transportation, dynamic electricity for auxiliary facilities, and lighting electricity, etc.); carbonaceous reducing agents (coke, under-sieve coke of ironmaking blast furnace, small particle coke for submerged arc furnace, and small particle semi-coke, etc.) consumption required for reducing ore, deducting the amount of secondary energy (such as: recovered gas and waste heat, etc.) that is recovered and externally supplied.

6.1.1.2 Statistical scope of smelting electricity consumption per unit product of ferroalloy

The smelting electricity consumption of ferroalloy products shall include electricity consumption for smelting and furnace-washing during the smelting of products, excluding electricity of the oven during production (the electricity of the oven refers to the electricity consumption to increase the hearth temperature by newly opened ferroalloy submerged arc

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. <https://www.ChineseStandard.us>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. <https://www.ChineseStandard.net>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies - <https://www.ChineseStandard.us>).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <https://www.chinesestandard.net/AboutUs.aspx>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <https://www.linkedin.com/in/waynezhengwenrui/>

----- The End -----