

Translated English of Chinese Standard: GB4544-2020

www.ChineseStandard.net → Buy True-PDF → Auto-delivery.

Sales@ChineseStandard.net

GB

NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA

ICS 55.100

Y 22

GB 4544-2020

Replacing GB 4544-1996

Beer bottles

啤酒瓶

Issued on: July 23, 2020

Implemented on: August 01, 2021

Issued by: State Administration for Market Regulation;

Standardization Administration of the People's Republic of China.

Table of Contents

Foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Product classification	5
5 Requirements	5
6 Test methods	8
7 Inspection rules for recycle new bottles and non-recycle bottles.....	10
8 Inspection rules for recycle used bottles	11
9 Marks, packaging, transportation, storage.....	12

Beer bottles

1 Scope

This Standard specifies the terms and definitions, product classification, requirements, test methods, inspection rules as well as marks, packaging, transportation and storage for glass beer bottles.

This Standard applies to glass bottles for beer.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

GB/T 2828.1, *Sampling procedures for inspection by attributes - Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*

GB/T 4545, *Test methods for stress examination of glass containers*

GB/T 4546, *Glass containers - Internal pressure resistance - Test methods*

GB/T 4547, *Glass containers - Test methods of the thermal shock resistance and thermal shock endurance*

GB/T 4548, *Test method and classification for hydrolytic resistance of the interior surfaces of glass containers*

GB/T 6552, *Glass containers - Test method for impact resistance*

GB/T 8452, *Test method for verticality of glass bottles*

GB/T 9987, *Glass contains - Manufacture - Vocabulary*

GB/T 20858, *Glass containers - Determination of capacity by gravimetric method - Test method*

GB/T 22934, *Glass containers - Resistance to vertical load - Test method*

GB/T 37855, *Glass containers - Dimensions for 26H126 crown finish*

GB/T 37856, *Glass containers - Dimensions for 26H180 crown finish*

3 Terms and definitions

For the purposes of this document, the terms and definitions defined in GB/T 9987 as well as the followings apply.

3.1 recycle beer bottle

Beer bottles that are designed to be refilled with beer multiple times.

3.2 recycle new bottle

Recycle beer bottles that have not yet been filled with beer, and can be handed over and accepted.

3.3 recycle used bottle

Recycle beer bottles that have already been filled with beer and can be refilled with beer.

3.4 non-recycle bottle

Beer bottles that are designed to be non-refillable.

4 Product classification

4.1 Beer bottles are classified into recycle beer bottles and non-recycle bottles according to the way they are used.

4.2 Recycle beer bottles can be divided into recycle new bottles and recycle used bottles according to the state of use.

5 Requirements

5.1 Physical and chemical properties

The physical and chemical properties shall meet the requirements in Table 1.

There shall be no calculus on the sealing surface.

There shall be no calculus with a diameter greater than 1.5 mm in the remaining parts. There are no more than 2 calculus with a diameter of 0.3 mm ~ 1.5 mm and no cracks around each bottle.

5.3.2 Cracks

There shall be none.

5.3.3 Air bubbles

There shall be no broken air bubbles and surface bubbles.

There shall be no air bubbles of which the diameter is greater than 3 mm. No more than 3 bubbles of which the diameter is 1 mm ~ 3 mm per bottle. For air bubbles below 1 mm, there are no more than 5 per square centimeter.

5.3.4 Defects of bottle mouth

There shall be no defects affecting the sealing and safe use on the sealing surface of the bottle mouth.

There shall be no flying thorns, poor forming and misalignment at the bottle mouth.

5.3.5 Inner wall defects

There shall be no sticky material, spikes, glass wires, and glass fragments on the inner wall of the bottle.

5.3.6 Sutures and surface defects

There shall be no sharp and prickly sutures and obvious initial sutures.

There shall be no severe and obvious streaks, cold spots, stains and other defects that seriously affect the appearance.

When necessary, it can also be subject to the sealed sample confirmed by both the supplier and the buyer.

5.3.7 Bottom knurling

There shall be knurling on the support surface of the bottom of the bottle.

6 Test methods

6.1 Physical and chemical properties

6.1.1 Vertical load strength

According to the provisions of GB/T 22934. Pressurize at a propulsion speed of 2 mm/min.

6.1.2 Resistance to internal pressure

According to the provisions of GB/T 4546.

6.1.3 Thermal shock resistance

According to the provisions of the passing test in GB/T 4547.

6.1.4 Shock resistance

According to the provisions of the passing test in GB/T 6552. During the impact test, the impact point is located in the middle of the bottle body, and the suture shall be avoided.

6.1.5 Internal stress

According to the provisions of GB/T 4545.

6.1.6 Water resistance of inner surface

According to the provisions of GB/T 4548.

6.2 Specifications and sizes**6.2.1 Mouthful capacity**

According to the provisions of GB/T 20858.

6.2.2 Bottle height

Measure with a height vernier caliper or a height measuring device with a graduation value of 0.02 mm.

6.2.3 Bottle outer diameter

Measure the maximum outer diameter of the bottle with a vernier caliper, gauge or other outer diameter measuring device of which the division value is 0.02 mm. Any point on the same cross-section shall meet the requirements.

6.2.4 Vertical axis deviation

According to the provisions of GB/T 8452.

6.2.5 Thickness of bottle body and bottom

7.3 Each item in each batch of inspection table 4 must be qualified. If there is an unqualified item, the responsible department shall decide to discard the batch or resubmit it for inspection after analyzing the specific unqualified situation. If the products resubmitted for inspection still do not meet the requirements, the batch shall be deemed as unqualified.

8 Inspection rules for recycle used bottles

8.1 Beer production enterprises shall ensure that the recycled bottles are all recycle used bottles. Carry out quality control inspection. Unqualified recycle used bottles cannot be used.

8.2 When the brewery recycles used bottles, it shall first conduct a preliminary appearance inspection of the recycle beer bottles.

8.3 Recycle used bottles that pass the initial inspection can be used in batches when filling. Batches can be determined by recycle used bottles of the same specification that are recycled on the same day or recycle used bottles of similar quality sorted into stacks.

8.4 When recycle used bottles enter the filling process after initial inspection, cleaning, and online inspection, quality control shall be carried out for some physical and chemical properties and serious defects in appearance of this batch of products. Quality control shall be carried out in accordance with the primary sampling plan for normal inspection stipulated in GB/T 2828.1. The test method shall be carried out according to the regulations in Chapter 6.

8.5 The acceptance quality limit (AQL) and inspection level of recycle used bottles submitted for inspection shall comply with the provisions in Table 5. All items listed in the inspection table 5 shall be qualified. If one item is unqualified, the batch shall be deemed unqualified.

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. <https://www.ChineseStandard.us>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. <https://www.ChineseStandard.net>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies - <https://www.ChineseStandard.us>).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <https://www.chinesestandard.net/AboutUs.aspx>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <https://www.linkedin.com/in/waynezhengwenrui/>

----- The End -----