

Translated English of Chinese Standard: GB/T13552-2023
www.ChineseStandard.net → Buy True-PDF → Auto-delivery.
Sales@ChineseStandard.net

GB

NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA

ICS 21.220.10

CCS G 42

GB/T 13552-2023

Replacing GB/T 13552-2008

Automotive V-ribbed belts

汽车多楔带

Issued on: September 07, 2023

Implemented on: April 01, 2024

**Issued by: State Administration for Market Regulation;
Standardization Administration of the People's Republic of China.**

Table of Contents

Foreword	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Structure	6
5 Model and marking	6
6 Cross-sectional dimensions	7
7 Requirements	7
8 Test methods	8
9 Inspection rules	9
10 Signs, labels, packaging, storage and transportation	10

Automotive V-ribbed belts

1 Scope

This document specifies the structure, model and marking, cross-sectional dimensions, requirements, test methods, inspection rules, signs, labels, packaging, storage and transportation of automotive V-ribbed belts (hereinafter referred to as "V-ribbed belts").

This document applies to V-ribbed belts for transmission of fans, motors, water pumps, compressors, power steering pumps, superchargers, etc. of automobile internal combustion engines.

This document does not apply to elastic V-ribbed belts.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

GB/T 3686, *V-belts -- Tensile strength and elongation test method*

GB/T 6931.1, *Belt drives -- Vocabulary -- Part 1: Basic vocabulary*

GB/T 6931.2, *Belt drives -- Vocabulary -- Part 2: V-belts and V-ribbed belt drives*

GB/T 10715, *Belt drives -- V-ribbed belts, joined V-belts and V-belts including wide section belts and hexagonal belts -- Electrical conductivity of antistatic belts: Characteristics and methods of test*

GB/T 17516.2, *V-and ribbed belts drive. Dynamic test to determine pitch zone location. Part 2: V-ribbed belts*

GB/T 33513, *Belt drives -- Pulleys and V-ribbed belts for the automotive industry - PK profile: Dimensions*

GB/T 41947, *Belt drives -- V-ribbed belts for the automotive industry -- Fatigue test*

3 Terms and definitions

For the purposes of this document, the terms and definitions defined in GB/T 6931.1, GB/T 6931.2 apply.

7.6 Antistatic properties

The antistatic properties of V-ribbed belts with antistatic requirements shall comply with the requirements of GB/T 10715.

8 Test methods

8.1 Appearance

Check the appearance of the V-ribbed belt by visual inspection.

8.2 Size

The effective line difference of V-ribbed belt is measured according to the provisions of GB/T 17516.2. The exposed height and effective length limit deviation of the V-ribbed belt are measured in accordance with the provisions of GB/T 33513.

8.3 Tensile property test

The tensile strength and reference force elongation of V-ribbed belts are tested in accordance with the provisions of GB/T 3686.

8.4 Low temperature resistance performance test

8.4.1 Specimen

The number of specimens is 3. Taken from the same sample tape. Cut a strip with a length of not less than 250 mm as a specimen. If 3 specimens cannot be taken from one sample belt, 3 specimens can be taken from the same model and batch of products, but this shall be noted in the test report.

8.4.2 Test procedures

For ordinary V-ribbed belts, the specimens are pretreated at a temperature of $(100\pm 2)^{\circ}\text{C}$ for 70^{+2}_{-0} h . The specimen is then cooled to room temperature and kept at $(-30\pm 1)^{\circ}\text{C}$ for 70^{+2}_{-0} h . For heat-resistant V-ribbed belts, pretreat the specimens for 70^{+2}_{-0} h at a temperature of $(120\pm 2)^{\circ}\text{C}$. The specimen is then cooled to room temperature and kept at a temperature of $(-40\pm 1)^{\circ}\text{C}$ for 70^{+2}_{-0} h . After taking it out, immediately conduct bending tests on the corresponding cylinders according to the requirements of Condition A and Condition B in Table 2. The bending arc must be at least 90° .

8.5 Fatigue life test

The length of the V-ribbed belt is based on the actual usage conditions or as agreed between the supplier and the purchaser. Use a two-wheel, three-wheel or four-wheel fatigue testing machine to conduct fatigue life testing in accordance with the provisions of GB/T 41947.

8.6 Antistatic performance test

The antistatic performance of V-ribbed belts is tested in accordance with the provisions of GB/T 10715.

9 Inspection rules

9.1 Exit-factory inspection

9.1.1 V-ribbed belts must be inspected by the manufacturer's quality inspection department and issued with a certificate before leaving the factory.

9.1.2 The exit-factory inspection items of V-ribbed belts include appearance, size and tensile properties.

9.1.3 V-ribbed belts shall be visually inspected one by one.

9.1.4 For the size of the V-ribbed belt, at least 3 shall be measured for each mold, and 1 shall be taken from the head, middle and tail. If one of them is unqualified, the molded V-ribbed belt shall be fully inspected.

9.1.5 The number of V-ribbed belts of the same material shall not exceed 50,000 in one batch. Sufficient samples shall be taken from each batch of products for tensile property testing. If the monthly output is less than 50,000 pieces, inspection will be conducted once a month. If the party has special requirements, relevant inspections can be decided through negotiation between the supplier and the purchaser.

9.2 Type inspection

9.2.1 V-ribbed belts shall undergo type inspection at least once every six months. When one of the following conditions occurs, type inspection shall be carried out.

- a) During the trial production of new products or the finalization and appraisal of old products for production transfer;

- b) When the product is resumed after 2 years of discontinuation;
- c) After the product is officially produced, if there are major changes in structure, materials, and processes, it may affect product performance;
- d) When the national market supervision and administration department puts forward requirements for type inspection.

9.2.2 The type inspection items of V-ribbed belts shall include all items in Chapter 7.

9.3 Determination rules

9.3.1 Exit-factory inspection

9.3.1.1 If one or both of the appearance and dimensions of the V-ribbed belt do not meet the requirements of this document, the product will be judged as unqualified.

9.3.1.2 If the tensile properties of the V-ribbed belt do not meet the requirements of this document, double the number of specimens from the batch of V-ribbed belt products shall be taken for re-inspection. If the re-inspection result is still unqualified, the batch of products will be judged as unqualified products.

9.3.2 Type inspection

9.3.2.1 The appearance and size determination of V-ribbed belts shall be carried out in accordance with 9.3.1.1.

9.3.2.2 If the tensile properties, low temperature resistance, fatigue life and antistatic properties of the V-ribbed belt do not meet the requirements of this document, double the number of specimens will be taken from the batch of V-ribbed belt products, and the unqualified items and related items will be reinspected. If one or more of the re-inspection results are still unqualified, the batch of products will be judged as unqualified.

10 Signs, labels, packaging, storage and transportation

10.1 Signs

Each V-ribbed belt shall be clearly marked and shall at least include the following:

- a) Mark;
- b) Manufacturer's name or trademark or supplier code;
- c) Year and month of manufacture or batch number.

10.2 Labels and packaging

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. <https://www.ChineseStandard.us>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. <https://www.ChineseStandard.net>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies - <https://www.ChineseStandard.us>).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <https://www.chinesestandard.net/AboutUs.aspx>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <https://www.linkedin.com/in/waynezhengwenrui/>

----- The End -----