

Translated English of Chinese Standard: GB/T22889-2021

www.ChineseStandard.net → Buy True-PDF → Auto-delivery.

Sales@ChineseStandard.net

GB

NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA

ICS 59.140.30

Y 46

GB/T 22889-2021

Replacing GB/T 22889-2008

**Leather - Physical and mechanical tests -
Determination of surface coating thickness**

皮革 物理和机械试验 表面涂层厚度的测定

(ISO 17186:2011, MOD)

Issued on: May 21, 2021

Implemented on: December 01, 2021

Issued by: State Administration for Market Regulation;

Standardization Administration of the PRC.

Table of Contents

Foreword.....	3
1 Scope.....	6
2 Normative references.....	6
3 Principle	6
4 Apparatus.....	6
5 Sampling and sample preparation	7
6 Test procedure	8
7 Result calculation	14
8 Test report	14

Foreword

This Standard is drafted in accordance with the rules given in GB/T 1.1-2009.

This Standard replaces GB/T 22889-2008 "Leather - Physical and mechanical tests - Determination of surface coating thickness". Compared with GB/T 22889-2008, in addition to editorial changes, the main technical changes of this Standard are as follows:

- Modify the expression method of the results in the "Principle" (see Clause 3; Clause 3 of the 2008 edition);
- Modify and refine the requirements for microscopes (see 4.1; 4.1 of the 2008 edition);
- Add apparatus such as razor blade, grid, and coating unit (see 4.2~4.5);
- Delete apparatus such as scalpel, tissue slicer, and micrometer (see 4.2~4.4 of the 2008 edition);
- Modify and refine the sample preparation method (see 5.3; 5.3~5.4 of the 2008 edition);
- Add the optional method of measurement in the test procedure; refine the test operations (see Clause 6; Clause 6 of the 2008 edition);
- Adjust the test report (see Clause 8; Clause 8 of the 2008 edition).

This Standard uses the redraft law to modify and adopt ISO 17186:2011 "Leather - Physical and mechanical tests - Determination of surface coating thickness".

Compared with ISO 17186:2011, the structural adjustments of this Standard are as follows:

- Divide 5.1 into "5.1 Sampling" and "5.2 Conditioning"; and change the following clause-subclause numbers in turn (see 5.1 and 5.2);
- Combine 5.2 and 5.3 into "5.3 Sample preparation" (see 5.3).

The technical differences between this Standard and ISO 17186:2011 and their reasons are as follows:

- As for the normative references, this Standard has made adjustments with technical differences, to adapt to the technical conditions of China. The adjustments are mainly reflected in Clause 2 "Normative references". The

specific adjustments are as follows:

- Replace ISO 2418 with GB/T 39364, which modifies and adopts the international standard (see 5.1 and Clause 8);
- Replace ISO 2419 with QB/T 2707, which modifies and adopts the international standard (see 5.2);
- Add the optional tool of the blade, which is in line with the current status of the leather industry and broadens the choice of cutting tools (see 4.2);
- Add the requirements for sampling at non-standard locations, to meet the needs of daily testing (or sampling directly from shoes and clothing) (see 5.1);
- Modify the size requirements for sample preparation, which is in line with current industry habits, enhances operability, and does not affect the test results (see 5.3);
- Delete the description of the confidence interval in the measurement principle method A, so that the standard text is unified before and after (see 6.1.1 of ISO 17186:2011);
- Add the marking of the measuring points in Figure 1, to facilitate the understanding and use of the standard (see Figure 1);
- Add the requirement for the total distance of six equidistant measuring points in method A measurement, to enhance the accuracy of the results (see 6.2.1.5 and 6.2.2.4);
- Add the requirements for the accuracy of the calculation results, which is in line with China's habits and enhances the comparability of results between laboratories (see Clause 7).

For ease of use, this Standard has also made the following editorial changes:

- Adjust part of the content in "1 Scope" to the note of "3 Principle" (see Clause 3);
- Modify the description method of eyepieces with scale (see 4.1);
- Add a subclause title to "5 Sampling and sample preparation" (see Clause 5);
- Add the number of formulas (see 6.2.1.9 and Clause 7);
- Simplify the description of 6.2.2.8 and 6.3.3.8 (see 6.2.2.8 and 6.3.3.8);

Leather - Physical and mechanical tests - Determination of surface coating thickness

1 Scope

This Standard specifies the test method for the surface coating thickness of leather.

This Standard applies to the determination of the surface coating thickness of all types of leather.

2 Normative references

The following documents are indispensable for the application of this document. For the dated references, only the editions with the dates indicated are applicable to this document. For the undated references, the latest edition (including all the amendments) are applicable to this document.

GB/T 39364 Leather - Chemical, physical, mechanical and fastness tests - Sampling location (GB/T 39364-2020, ISO 2418:2017, MOD)

QB/T 2707 Leather - Physical and mechanical tests - Sample preparation and conditioning (QB/T 2707-2018, ISO 2419:2012, MOD)

3 Principle

A section of leather is taken perpendicular to the coated surface. The thickness of the surface coating is measured using a microscope and expressed both as a thickness and as a percentage to the total thickness.

Note: This method measures the surface coating thickness of the leather under zero compression.

4 Apparatus

4.1 Light microscope or scanning electron microscope, capable of operating within a field of view of 1 mm×1 mm or less and meeting any of the following conditions:

- Equipped with a camera image unit connected to a computer (with a

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. <https://www.ChineseStandard.us>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. <https://www.ChineseStandard.net>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies - <https://www.ChineseStandard.us>).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <https://www.chinesestandard.net/AboutUs.aspx>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <https://www.linkedin.com/in/waynezhengwenrui/>

----- The End -----