

Translated English of Chinese Standard: GB/T23456-2018

www.ChineseStandard.net → Buy True-PDF → Auto-delivery.

Sales@ChineseStandard.net

GB

NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA

ICS 91.100.10

Q 62

GB/T 23456-2018

Replacing GB/T 23456-2009

Phosphogypsum

磷石膏

Issued on: June 7, 2018

Implemented on: May 1, 2019

Issued by: State Administration for Market Regulation;

Standardization Administration of the People's Republic of China.

Table of Contents

Foreword.....	3
1 Scope.....	5
2 Normative References.....	5
3 Classification and Labeling.....	5
4 Requirements	5
5 Test Methods	6
6 Inspection Rules.....	7
7 Packaging, Marking, Transportation and Storage.....	8

Phosphogypsum

1 Scope

This Standard specifies the classification and labeling, requirements, test methods, inspection rules, as well as packaging, marking, transportation and storage of phosphogypsum.

This Standard is applicable to phosphogypsum, which is obtained when phosphoric acid is produced through the wet method, using phosphate ore as the raw material, and with calcium sulfate dihydrate ($\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$) as the main component.

2 Normative References

The following documents are indispensable to the application of this document. In terms of references with a specified date, only versions with a specified date are applicable to this document. In terms of references without a specified date, the latest version (including all the modifications) is applicable to this document.

GB/T 5484-2012 Methods for Chemical Analysis of Gypsum

GB 6566 Limits of Radionuclides in Building Materials

JC/T 2073 Determination of Phosphorus and Fluorine Content in Phosphogypsum

3 Classification and Labeling

3.1 Classification

In accordance with the content of calcium sulfate dihydrate, from high to low, the product is mainly classified into Grade-1, Grade-2 and Grade-3.

3.2 Labeling

Labeling is performed in accordance with the sequence of product name, standard serial No. and classification.

EXAMPLE: Grade-1 phosphogypsum is labeled as follows: Phosphogypsum GB/T 23456-2018 Grade-1.

4 Requirements

4.1 Basic Requirements

5.2.2 Calculation of calcium sulfate dihydrate ($\text{CaSO}_4 \bullet 2\text{H}_2\text{O}$) content

The content of calcium sulfate dihydrate ($\text{CaSO}_4 \bullet 2\text{H}_2\text{O}$) is calculated in accordance with Formula (1), and the calculation result is accurate to 0.01%.

$$G = 4.7785 \times H \quad \dots\dots\dots (1)$$

Where,

G ---the content of calcium sulfate dihydrate ($\text{CaSO}_4 \bullet 2\text{H}_2\text{O}$), expressed in (%);

4.7785---the coefficient of converting the crystallization water content into calcium sulfate dihydrate ($\text{CaSO}_4 \bullet 2\text{H}_2\text{O}$) content;

H ---the content of crystallization water, expressed in (%).

5.3 Water-soluble Phosphorus Pentoxide (P_2O_5)

Carry out the test in accordance with JC/T 2073.

5.4 Water-soluble Fluoride Ions (F^-)

Carry out the test in accordance with JC/T 2073.

5.5 Water-soluble Magnesium Oxide (MgO)

Carry out the test in accordance with Chapter 27 of GB/T 5484-2012.

5.6 Water-soluble Sodium Oxide (Na_2O)

Carry out the test in accordance with Chapter 28 of GB/T 5484-2012.

5.7 Chloride Ions (Cl^-)

Carry out the test in accordance with Chapter 29 of GB/T 5484-2012.

5.8 Limits of Radionuclides

Carry out the test in accordance with GB 6566.

5.9 pH Value

Carry out the test in accordance with Chapter 25 of GB/T 5484-2012.

6 Inspection Rules

6.1 Inspection Classification

6.1.1 Exit-factory inspection

The exit-factory inspection items are attached water (H_2O), calcium sulfate dihydrate ($\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$) content, water-soluble phosphorus pentoxide (P_2O_5), water-soluble fluoride ions (F^-) and pH value.

6.1.2 Type inspection

The type inspection items all items specified in Chapter 4. Under one of the following circumstances, type inspection shall be carried out:

- a) When there are major changes in raw materials, processes and equipment;
- b) When the production is resumed after being discontinued for more than half a year;
- c) After one year of normal production.

6.2 Batch Size and Sampling

6.2.1 Batch size

5,000 t of products are considered as one batch, and products less than 5,000 t are also counted as one batch.

6.2.2 Sampling

When sampling from the stockyard, the outer layer of the material about 500 mm thick shall be removed, more than 20 different parts shall be selected, and a total of about 10 kg of specimens shall be taken. After mixing, divide the specimens into 2 kg using the quartering method. Divide the sample taken into two equal parts, one as the test sample and the other as the backup sample; keep them sealed.

6.3 Determination

If the inspection results comply with all the requirements in Chapter 4, then, the batch of products shall be determined as qualified. If two or more items (including two items) fail to satisfy the requirements, then, the batch of products shall be determined as disqualified. If only one item is disqualified, then, use the backup sample to conduct a re-inspection on the disqualified item. If it passes the re-inspection, then, the batch of products shall be determined as qualified; if it still fails, then, the batch of products shall be determined as disqualified.

7 Packaging, Marking, Transportation and Storage

7.1 Packaging

The products can be supplied in bulk or packages.

7.2 Marking

Products leaving the factory shall be accompanied by a product inspection certificate. The

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. <https://www.ChineseStandard.us>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. <https://www.ChineseStandard.net>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies - <https://www.ChineseStandard.us>).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <https://www.chinesestandard.net/AboutUs.aspx>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <https://www.linkedin.com/in/waynezhengwenrui/>

----- The End -----