Translated English of Chinese Standard: GB/T23906-2009

<u>www.ChineseStandard.net</u> → Buy True-PDF → Auto-delivery.

<u>Sales@ChineseStandard.net</u>

GB

# NATIONAL STANDARD OF THE PEOPLE'S REPUBLIC OF CHINA

ICS 19.100

J 04

GB/T 23906-2009

# Non-destructive testing - Rings for magnetic particle testing

无损检测 磁粉检测用环形试块

Issued on: May 26, 2009 Implemented on: September 01, 2009

Issued by: General Administration of Quality Supervision, Inspection and Quarantine;
Standardization Administration of the People's Republic of China.

# **Table of Contents**

Foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Classification	4
5 Technical requirements	5
6 Test methods	7
7 Inspection rules	8
8 Mark	10
9 Marking and labeling	11
10 Packaging, transportation and storage	11
References	12

# Non-destructive testing - Rings for magnetic particle testing

# 1 Scope

This Standard specifies the classification, technical requirements and inspection methods of rings (or blocks) for magnetic particle testing.

This Standard applies to the type inspection and exit-factory inspection of rings. This Standard can also be used as the acceptance basis for user orders.

## 2 Normative references

The terms in the following documents become the terms of this Standard by reference to this Standard. For dated references, all subsequent amendments (not including errata content) or revisions do not apply to this standard. However, parties to agreements that are based on this Standard are encouraged to study whether the latest versions of these documents can be used. For undated references, the latest edition applies to this Standard.

GB/T 699-1999, Quality carbon structural steels

GB/T 1299-2000, Alloy tool steels

GB/T 12604.5, Non-destructive testing - Terminology - Magnetic particle testing

GB/T 19001, Quality management systems - Requirements (GB/T 19001-2008, ISO 9001:2008, IDT)

GB/T 27025, General requirements for the competence of testing and calibration laboratories (GB/T 27025-2008, ISO/IEC 17025:2005, IDT)

# 3 Terms and definitions

Terms and definitions determined by GB/T 12604.5 are applicable to this Standard.

## 4 Classification

Rings, to which this Standard is applicable, shall be classified as follows:

- a) Type B test block (or DC ring);
- b) Type E test block (or AC ring).

- $1\sim3$  through-holes, the diameter of which is  $(1^{+0.08}_{-0.05})$  mm.
- 4 − type E test block;
- 5 insulating bushing;
- 6 conductive mandrel.

The allowable tolerance of  $l_i$  is  $\pm 0.05$ mm.

The allowable tolerance of the included angle of the through-hole is  $\pm 0.5^{\circ}$ , and the allowable tolerance of each circle center is  $\pm 0.5$  mm.

## Figure 2 – Type E test block

## 6 Test methods

#### 6.1 Chemical composition and grain size

An appropriate method shall be used for determination.

## 6.2 Hardness and surface roughness

An appropriate method shall be used for determination.

#### 6.3 Through-hole angle (two surfaces)

An appropriate method with an accuracy better than  $\pm 0.1^{\circ}$  shall be used for determination.

#### 6.4 Size

- **6.4.1** An appropriate method with an accuracy better than  $\pm 0.01$  mm shall be used to measure the through-hole diameter, and the distance from the through-hole center to the outer ring edge (two surfaces).
- **6.4.2** An appropriate method with an accuracy better than  $\pm 0.1$  mm shall be used to measure the distance between the centers of two adjacent through-holes (two surfaces), the outer diameter, inner diameter and thickness of the test block, the outer diameter, inner diameter and thickness of the insulating bushing, and the diameter and length of the conductive mandrel.
- **6.4.3** An appropriate method shall be used to measure the tightness (between the test block and the insulating bushing, or between the insulating bushing and the conductive mandrel), the concentricity between the test block and the conductive mandrel.

# 7 Inspection rules

#### 7.1 Batch rules

#### 7.1.1 Materials

Each batch consists of the quantity of materials of the same heat number and the same heat treatment (annealed or unannealed) state.

#### 7.1.2 Test block

Each batch consists of a ring individually.

## 7.2 Inspection classification

## 7.2.1 Type inspection

Type inspection should be carried out in any of the following situations:

- a) during new production, production change or resumption of production after suspension;
- b) when materials or processes are changed;
- c) when it is stipulated in the contract;
- d) when it is more than 24 months since the last type inspection.

The type inspection of the rings shall be carried out by a laboratory with ring type inspection and testing items approved by GB/T 27025<sup>1</sup>. The type inspection laboratory shall issue an inspection report on the implementation of this Standard.

## 7.2.2 Exit-factory inspection (or batch inspection)

The manufacturer of the rings shall carry out exit-factory inspection for each ring product, and issue an inspection certificate on the implementation of this Standard.

The exit-factory inspection shall be defined and guaranteed by the quality system. The system should meet the requirements of GB/T 19001.

### 7.3 Inspection items

## 7.3.1 Type B test block

See Table 1 for the inspection items of type B test block.

<sup>&</sup>lt;sup>1</sup> The list of relevant laboratories can be obtained from the Secretariat of the National Technical Committee 56 on Non-destructive testing of Standardization Administration of China (http://www.chinadt.org.cn).

B – Type B test block.

# 9 Marking and labeling

- **9.1** The marking or labeling of rings shall contain at least:
  - a) manufacturer's name, trademark or identification mark, detailed address;
  - b) product name, model and specification, product standard number, place of origin;
  - c) traceable product number.
- **9.2** The marking or labeling shall be seen on the packaging.

# 10 Packaging, transportation and storage

- **10.1** After the ring is treated with anti-rust, each piece should be packed in a hard box separately to prevent the test block from rusting and damage.
- **10.2** The manufacturer shall indicate the requirements for transportation and storage on the packaging to avoid damage to the rings.
- **10.3** The documents accompanied when the product is delivered shall include:
  - a) product certificate;
  - b) product instruction manual;
  - c) type inspection report (when agreed in the contract);
  - d) exit-factory inspection certificate (when agreed in the contract).

# This is an excerpt of the PDF (Some pages are marked off intentionally)

# Full-copy PDF can be purchased from 1 of 2 websites:

# 1. https://www.ChineseStandard.us

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

# 2. <a href="https://www.ChineseStandard.net">https://www.ChineseStandard.net</a>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies https://www.ChineseStandard.us).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <a href="https://www.chinesestandard.net/AboutUs.aspx">https://www.chinesestandard.net/AboutUs.aspx</a>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <a href="https://www.linkedin.com/in/waynezhengwenrui/">https://www.linkedin.com/in/waynezhengwenrui/</a>

---- The End -----