

Translated English of Chinese Standard: GB/T38510-2020

www.ChineseStandard.net → Buy True-PDF → Auto-delivery.

Sales@ChineseStandard.net

GB

NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA

ICS 83.160.10

G 41

GB/T 38510-2020

**Evaluation of self-sealing performance for tyres
coated with self-sealing material**

涂覆式刺扎自密封轮胎自密封性能评价

Issued on: March 06, 2020

Implemented on: February 01, 2021

Issued by: State Administration for Market Regulation;

**Standardization Administration of the People's Republic of
China.**

Table of Contents

Foreword	3
Introduction.....	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Evaluation requirements.....	6
5 Test methods	7
Annex A (informative) Identification and warning information.....	9
Annex B (normative) Test nails and puncturing method.....	10

Evaluation of self-sealing performance for tyres coated with self-sealing material

1 Scope

This Standard specifies the evaluation requirements and test methods for self-sealing performance of tyres coated with self-sealing material.

This Standard applies to pneumatic tubeless passenger car radial tyres with a coating inside the crown and with anti-leakage function after puncturing.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

GB/T 4502 Laboratory test methods for passenger car tyres capabilities

GB/T 6326 Tyre terms and definitions

GB 9743 Passenger car tyres

3 Terms and definitions

For the purpose of this document, the terms and definitions defined in GB/T 6326 and the following apply.

3.1

tyres coated with self-sealing material

Tyres of which the inner side of the crown is coated with self-sealing material. After the crown is punctured by foreign matters (diameter not greater than 5 mm), whether the foreign matters are pulled out or remain in the crown, the tyres still have a good sealing performance.

5 Test methods

5.1 Static airtightness

5.1.1 Static airtightness test at indoor normal temperature

INSTALL the test tyre on the measuring rim; FILL it with 250 kPa air pressure. After placing at the test ambient temperature of $23\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ for 3 h, the air pressure of the test tyre is re-calibrated to 250 kPa. PUNCTURE with nails according to the requirements of Annex B. After placing for 24 h, PULL OUT all the nails. After 24 h, MEASURE and RECORD the air pressure again.

5.1.2 Static airtightness test at indoor low temperature

INSTALL the test tyre on the measuring rim; FILL it with 250 kPa air pressure. After placing at room temperature for 3 h, MEASURE and RECORD the air pressure value of the tyre. SET the temperature of the low temperature refrigeration device (temperature control range $-40\text{ }^{\circ}\text{C} \sim 0\text{ }^{\circ}\text{C}$) to $-25\text{ }^{\circ}\text{C}$. After the temperature is constant, PUT the tyre in and continue to freeze for not less than 12 h. REMOVE the tyre, PUNCTURE it with the nails that have been frozen at the same low temperature for more than 12 h as soon as possible according to the requirements of Annex B, and PULL OUT all the test nails within 3 min. Then PUT the tyre into the same low temperature environment as above and continue to freeze for more than 12 h. REMOVE the tyre and leave it at room temperature for 24 h. MEASURE and RECORD the air pressure value of the tyre again.

5.2 Endurance test

5.2.1 Nail-pull-out endurance test

The test tyre is punctured with nails according to the requirements of Annex B, and then immediately pull out all the nails. After placing for 3 h, carry out the endurance test according to GB/T 4502.

5.2.2 Nail-not-pull-out endurance test

The test tyre is punctured with nails according to the requirements of Annex B. After placing for 3 h, carry out the endurance test according to GB/T 4502.

5.3 High-speed performance test

The test tyre is punctured with nails according to the requirements of Annex B, and then immediately pull out all the nails. After placing for 3 h, carry out the high-speed performance test according to GB/T 4502.

5.4 Outdoor low-temperature road endurance performance test

5.4.1 Test requirements

This test is only carried out when the coating formulation, production process changes or when it is re-produced. Test tyres shall be snow tyres or icy tyres.

5.4.2 Test procedure

5.4.2.1 INSTALL four test tyres on the rim used by the test vehicle; FILL them with 250 kPa air pressure.

5.4.2.2 The inflated test tyre rim assembly is placed at an ambient temperature of $-35\text{ }^{\circ}\text{C} \sim -20\text{ }^{\circ}\text{C}$ for more than 3 h.

5.4.2.3 According to the requirements of Annex B, the four tyres are punctured with nails. The nails of two tyres are pulled out, and the nails of the other two tyres are not pulled out.

5.4.2.4 INSTALL the two nail-not-pull-out tyres on the front axle of the test vehicle, and the two nail-pull-out tyres on the rear axle of the test vehicle. The test load carried by the test tyres on both sides of each axle shall be 60 % to 80 % of the load capacity corresponding to its load index.

5.4.2.5 RECALIBRATE the air pressure of the test tyres to 250 kPa.

5.4.2.6 At an ambient temperature of $-35\text{ }^{\circ}\text{C} \sim -20\text{ }^{\circ}\text{C}$, the test vehicle travels for a total of 800 km at a speed of (80 ± 10) km/h, and the air pressure of the tyres is measured and recorded for every (100 ± 10) km on the way. After the 800 km driving distance is over, the vehicle is parked at an ambient temperature of $-35\text{ }^{\circ}\text{C} \sim -20\text{ }^{\circ}\text{C}$ for more than 3 h, and the air pressure of the tyres is measured again and recorded.

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. <https://www.ChineseStandard.us>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. <https://www.ChineseStandard.net>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies - <https://www.ChineseStandard.us>).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <https://www.chinesestandard.net/AboutUs.aspx>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <https://www.linkedin.com/in/waynezhengwenrui/>

----- The End -----