

Translated English of Chinese Standard: GB/T3903.26-2020

www.ChineseStandard.net → Buy True-PDF → Auto-delivery.

Sales@ChineseStandard.net

GB

NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA

ICS 61.060

Y 78

GB/T 3903.26-2020 / ISO 20863:2018

Replacing GB/T 3903.26-2008

**Foot wear - Test methods for stiffeners and toepuffs -
Bondability**

鞋类 主跟和包头试验方法 粘合性能

(ISO 20863:2018, IDT)

Issued on: October 21, 2020

Implemented on: May 01, 2021

**Issued by: State Administration for Market Regulation;
Standardization Administration of the People's Republic of
China.**

Table of Contents

Foreword.....	3
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	5
4 Test equipment and materials	5
5 Sampling and conditioning.....	6
6 Test method	7
7 Test result.....	8
8 Test report.....	9
Appendix NA (Informative) Technical data of the Test material L1	10
References	11

Foreword

This Standard was drafted in accordance with the rules given in GB/T 1.1-2009.

This Standard replaces GB/T 3903.26-2008 "Footwear - Test methods for stiffeners and toepuffs - Bondability"; compared with GB/T 3903.26-2008, the major technical changes are as follows:

- Modify normative references (see Chapter 2; Chapter 2 of version 2008);
- Add a footnote (see 4.3.2; 4.3.2 of version 2008);
- Modify requirements for the reference leather (see 4.4; 4.4 of version 2008);
- Add requirements for acetone or other organic solvent type ketones (see 4.7);
- Modify requirements for the number of samples (see 5.1; 5.1.1 of version 2008);
- Modify requirements for the heating time (see 5.1.4; 5.1.4 of version 2008);
- Modify requirements for the unstuck length of the sample (see 5.2.3; 5.2.3 of version 2008);
- Modify requirements for the soaking time (see 6.5; 6.5 of version 2008);
- Change intermediate value of force to average value of force (see Figure 1; Figure 1 of version 2008);
- Change wet adhesion to wet bondability (see 7.2.2; 7.2.2 of version 2008);
- Modify requirements for the test report (see Chapter 8; Chapter 8 of version 2008);

The translation method used in this Standard is equivalent to ISO 20863:2018 "Footwear - Test methods for stiffeners and toepuffs - Bondability".

The documents of our country that have a consistent correspondence with the international documents that are referenced in this Standard are as follows:

- GB/T 16825.1-2008 Verification of static uniaxial testing machines - Part 1: Tension/compression testing machines - Verification and calibration of the force-measuring system (ISO 7500-1:2004, IDT)
- GB/T 22049-2019 Footwear - Standard atmospheres for conditioning and testing of footwear and components for footwear (ISO 18454:2018, IDT)

Foot wear - Test methods for stiffeners and toepuffs - Bondability

1 Scope

This Standard specifies test methods for the bondability of heat activated and solvent activated stiffeners and toepuffs to upper and lining materials.

This Standard applies to stiffeners and toepuffs for foot wear.

2 Normative references

The following documents are indispensable for the application of this document. For dated references, only the dated version applies to this document. For undated references, the latest edition (including all amendments) applies to this document.

ISO 7500-1 Metallic materials - Calibration and verification of static uniaxial testing machines - Part 1: Tension/compression testing machines - Calibration and verification of the force-measuring system

ISO 18454 Footwear - Standard atmospheres for conditioning and testing of footwear and components for footwear

3 Terms and definitions

The following terms and definitions are applicable to this document.

3.1

Bondability

The ability of a material to bond with itself or other materials through pressure and/or heating and the use of uniform adhesives.

4 Test equipment and materials

The following equipment and materials shall be used:

4.1 Tensile testing machine: with a jaw separation rate of 100 mm/min $\pm$ 10 mm/min, an applicable force range (this will usually be less than 100 N),

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. <https://www.ChineseStandard.us>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. <https://www.ChineseStandard.net>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies - <https://www.ChineseStandard.us>).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <https://www.chinesestandard.net/AboutUs.aspx>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <https://www.linkedin.com/in/waynezhengwenrui/>

----- The End -----