

Translated English of Chinese Standard: GB/T41747-2022
www.ChineseStandard.net → Buy True-PDF → Auto-delivery.
Sales@ChineseStandard.net

GB

NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA

ICS 77.140.50

CCS H 46

GB/T 41747-2022

**Continuous hot-dip zinc-coated twin-roll cast steel sheet
and strip of structural quality and high strength steel**

结构级和高强度连续热镀锌双辊铸轧薄钢板及钢带

(ISO 15211:2012, Continuous hot-dip zinc-coated twin-roll cast steel sheet of
structural quality and high strength steel, MOD)

Issued on: October 12, 2022

Implemented on: October 12, 2022

**Issued by: State Administration for Market Regulation;
Standardization Administration of the People's Republic of China.**

Table of Contents

Foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	6
4 Dimensions, shape, mass	7
5 Technical requirements	8
6 Test methods	12
7 Inspection rules	12
8 Classification and code	13
9 Packaging, marking and quality certificate	15
10 Order contents	15
Appendix A (informative) Structural changes of this document compared with ISO 15211:2012	17
Appendix B (informative) Technical differences between this document and ISO 15211:2012 and their reasons	19
Appendix C (informative) Approximate designations comparison table	22

Continuous hot-dip zinc-coated twin-roll cast steel sheet and strip of structural quality and high strength steel

1 Scope

This document specifies the dimensions, shape, mass, technical requirements, test methods, inspection rules, classification and code, packaging, marking, quality certificate and order contents of continuous hot-dip zinc-coated steel sheets and strips of structural quality and high strength steel produced by twin-roll casting process.

The products corresponding to this document are applied to inner and outer covering parts and structural parts that require corrosion resistance. This document applies to continuous hot-dip zinc-coated twin-roll cast steel sheets and strips of structural quality and high strength steel with a thickness not greater than 2.0 mm (hereinafter referred to as “steel sheets and strips”).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

GB/T 222 Permissible tolerances for chemical composition of steel products

GB/T 223.12 Methods for chemical analysis of iron, steel and alloy - The sodium carbonate separation-diphenyl carbazide photometric method for the determination of chromium content

GB/T 223.14 Methods for chemical analysis of iron, steel and alloy - The N-benzoyl-N-phenylhydroxylamine extraction photometric method for the determination of vanadium content

GB/T 223.18 Methods for chemical analysis of iron, steel and alloy - The sodium thiosulfate separation iodimetric method for the determination of copper content

GB/T 223.23 Iron, steel and alloy - Determination of nickel content - The dimethylglyoxime spectrophotometric method

GB/T 223.26 Iron, steel and alloy - Determination of molybdenum content - The thiocyanate spectrophotometric method

GB/T 20123 Steel and iron - Determination of total carbon and sulfur content - Infrared absorption method after combustion in an induction furnace (routine method)

GB/T 20124 Steel and iron - Determination of nitrogen content - Thermal conductimetric method after fusion in a current of inert gas (routine method)

GB/T 20125 Low-alloy steel - Determination of multi-element contents - Inductively coupled plasma atomic emission spectrometric method

GB/T 25052 Continuously hot-dip coated steel sheet and strip - Tolerances on dimensions, shape and mass

3 Terms and definitions

For the purpose of this document, the following terms and definitions apply.

3.1

twin-roll cast steel sheet and strip

Steel sheet and strip produced by the twin-roll casting process to cast into a cast strip with a thickness near the final thickness directly from the liquid metal, and subsequently hot-rolled with a small reduction.

3.2

continuous hot-dip zinc-coated steel sheet and strip

Product obtained by hot-dip coating of descaled twin-roll cast steel sheets and strips (3.1) or subsequent cold-rolled steel sheets and strips on a continuous zinc-coating line.

3.3

normal spangle coating

Coating with obvious spangle morphology, formed as a result of unrestricted growth of zinc grains during normal solidification process of zinc layer.

NOTE: Normal spangles have metallic luster and are widely used. It may be supplied as coating condition S or N (see 8.5); however, its appearance may be variable, and it is not suitable for decorative coating.

3.4

minimized spangle coating

Fine spangle coating that is formed by artificially restricting the zinc grains formed during solidification process of zinc layer.

NOTE: The surface appearance of this product may have some unevenness in the coating on a single coil or from coil to coil.

3.5

zero spangle coating

Fine spangle coating that is invisible to the naked eye, obtained through a special control method.

3.6

differential coating

Coating having different specified zinc layer masses on the two surfaces of zinc-coated steel sheet.

3.7

skin pass

Process of light cold rolling of zinc-coated steel sheet.

NOTE: The purpose of skin pass is to make the surface smoother to improve the surface appearance. Skin pass also temporarily reduces the occurrence of stretcher strain (Lüders lines) on the surface during fabrication of finished parts. The skin pass also controls and improves roughness. The skin pass results in an increase in hardness and a decrease in ductility.

4 Dimensions, shape, mass

4.1 The thickness of steel sheets and strips shall not exceed 2.0 mm, and width shall not exceed 1800 mm.

4.2 Zinc-coated steel sheets with a width of less than 900 mm may be cut from wide sheets.

4.3 The thickness of steel sheets and strips is the sum of the thickness of substrate and coating.

4.4 The dimensions, shape, mass and allowable deviation of steel sheets and strips shall comply with the provisions of GB/T 25052.

7.2 Steel sheets and strips shall be checked and accepted in batches, and each batch shall consist of steel products of the same designation, same furnace number, same specification and same delivery status.

7.3 The re-inspection and determination rules for steel sheets and strips shall comply with the provisions of GB/T 17505.

7.4 The measured values of various inspections and checks of steel sheets and strips shall be rounded off according to the rounding off value comparison method, and the rounding off rules shall comply with the provisions of GB/T 8170.

8 Classification and code

8.1 Designation naming method

8.1.1 General

The designation of steel sheets and strips are composed of steel use or characteristic code, steel grade code, steel characteristics, hot-dip code (D) and coating type code, where the hot-dip code (D) and coating type code are connected by “+”.

8.1.2 Steel type use code

SU: Indicates that it is structural quality steel.

HU: Indicates that it is high strength steel.

8.1.3 Steel grade code

280 ~ 650: 3 digits, used to represent the steel grade code, generally specified as the minimum yield strength, in megapascal (MPa).

8.1.4 Steel type characteristics code

G: Indicates that the steel type is uncertain.

LA: Indicates that the steel type is low alloy steel.

8.1.5 Hot-dip code

The hot-dip code is D.

8.1.6 Coating type code

The zinc-coated coating is denoted as Z.

8.2 Examples of designation naming

- Normal spangle, N;
- Normal spangle (skin pass), S;
- Minimized spangle, M;
- Minimized spangle (skin pass), E;
- Zero spangle, F.

8.6 Classification and code of surface treatment

The classification and code of surface treatment are as follows:

- Chromium-free passivation, CN;
- Chromic acid passivation, C;
- Phosphating, P;
- Oiling, O;
- Passivation oiling CO.

9 Packaging, marking and quality certificate

The packaging, marking and quality certificate of steel sheets and strips shall comply with the provisions of GB/T 247. If the purchaser has special requirements on packaging, it can be negotiated when ordering.

10 Order contents

When ordering, the purchaser shall provide the following information and indicate them in the contract:

- a) the serial number of this document;
- b) the product name;
- c) the designation;
- d) the coating type and coating mass code;
- e) the dimensions and their precision (including thickness, width, length, inner diameter of steel strips, etc.);
- f) the surface treatment;

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. <https://www.ChineseStandard.us>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. <https://www.ChineseStandard.net>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies - <https://www.ChineseStandard.us>).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <https://www.chinesestandard.net/AboutUs.aspx>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <https://www.linkedin.com/in/waynezhengwenrui/>

----- The End -----