

Translated English of Chinese Standard: GBT44553-2024

www.ChineseStandard.net → Buy True-PDF → Auto-delivery.

Sales@ChineseStandard.net

GB

NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA

ICS 77.010

CCS H 04

GB/T 44553-2024

**Technical specification for energy-saving of hot-dip
galvanizing thermal system for steel tubes
钢管热镀锌热工系统节能技术规范**

Issued on: September 29, 2024

Implemented on: April 1, 2025

**Issued by: State Administration for Market Regulation;
Standardization Administration of PRC.**

Table of Contents

Foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Technical requirements	5
4.1 General	5
4.2 Galvanizing furnace body, combustion system and control system	6
4.3 Waste heat system	8
5 Evaluation of operation energy efficiency indicators of thermal system	10

Technical specification for energy-saving of hot-dip galvanizing thermal system for steel tubes

1 Scope

This document specifies the technical requirements and operation energy efficiency index evaluation of the hot-dip galvanizing thermal system for steel tubes.

This document is applicable to the design, construction and operation energy efficiency evaluation of new construction, expansion and renovation projects of hot-dip galvanizing thermal systems for steel tubes.

2 Normative references

The provisions of the following documents constitute the essential clauses of this document through normative references in this text. Among them, for referenced documents with dates, only the versions corresponding to the dates are applicable to this document; for referenced documents without dates, the latest versions (including all amendments) are applicable to this document.

GB/T 2589 General rules for calculation of the comprehensive energy consumption

GB/T 8722 Test method for thermal conductivity of carbon materials

GB/T 10863 Thermal test method for gas pass heat recovery boiler

GB/T 13296 Seamless stainless steel tubes for boiler and heat exchanger

GB/T 16618 General principles for thermal insulation technique of industrial furnaces

GB 24500 Minimum allowable values of energy efficiency and energy efficiency grades of industrial boilers

GB/T 24593 Welded austenitic stainless steel tubes for boiler and heat exchanger

GB/T 27698.3 Test methods for the performance of heat exchangers and heat exchange elements - Part 3: Heat exchanger elements

GB/T 28056 General specification for gas pass heat recovery boiler

GB/T 28475.2 Microprocessor control equipment in industrial stove - Part 2:

steam in the heat recovery steam generator to blow the inner wall of the steel tube and dry the galvanized steel tube. The excess steam heats the solvent and pickling medium (hydrochloric acid or sulfuric acid) in the heat exchanger, or heats the circulating water and then heats the solvent and pickling medium (hydrochloric acid or sulfuric acid) in the heat exchanger. If there is excess heat, it is transported to the office area and living area for use.

4.2 Galvanizing furnace body, combustion system and control system

4.2.1 Energy selection

The heating energy of the galvanizing furnace shall be natural gas, liquefied petroleum gas, other clean energy or new energy. When natural gas is used for heating, the calorific value and pressure shall meet the following requirements:

- a) The heat output is stable, and the fluctuation range allowed during production is within $\pm 10\%$;
- b) The pressure is stable, and the allowable fluctuation range of the workshop gas contact pressure is within $\pm 5\%$.

4.2.2 Furnace type selection and main structure design

4.2.2.1 The furnace type can be a flat flame galvanizing furnace or a high-speed pulse galvanizing furnace.

4.2.2.2 The furnace body may adopt an I-shaped or U-shaped steel structure frame, and the furnace width should not exceed 1650 mm.

4.2.2.3 The zinc pot shall be equipped with a supporting device.

4.2.2.4 The galvanizing furnace shall be equipped with a zinc leakage pit of reasonable capacity.

4.2.3 Galvanizing furnace insulation

4.2.3.1 The side walls and furnace roof shall be made of ceramic fiber products, and the outer surface temperature of the furnace wall shall comply with the provisions of GB/T 16618.

4.2.3.2 On the premise of meeting the performance requirements such as temperature and load bearing, the furnace bottom masonry materials shall also be selected based on insulation effect, service life and economic rationality.

4.2.3.3 When refractory bricks and thermal insulation bricks are used to build the furnace bottom, the length and width of the refractory brick masonry are recommended

to be integer multiples of 116 mm, and the masonry height is recommended to be an integer multiple of 68 mm.

4.2.3.4 When refractory castables are used to cast the furnace bottom as a whole, the temperature and load-bearing requirements shall be met.

4.2.4 Galvanizing furnace heat load

4.2.4.1 The zinc capacity of the zinc pot should be 15~20 times the designed production capacity per unit time.

4.2.4.2 The average heating intensity of the zinc pot wall shall not be less than 24 kW/(m² • h).

4.2.4.3 The combustion device of appropriate specifications shall be selected according to the type and structural size of the galvanizing furnace, heating process, fuel type, heat load size and environmental protection requirements.

4.2.4.4 The heat supply of the galvanizing furnace shall be determined by heat balance calculation or selected according to empirical data.

4.2.4.5 The maximum heat load of the galvanizing furnace shall not exceed 1.3 times the rated heat load.

4.2.5 Energy saving of galvanizing furnace

4.2.5.1 The exhaust gas temperature of the galvanizing furnace should not exceed 600 °C, and the waste heat shall be recycled.

4.2.5.2 It is recommended to use a computer control system for the thermal system of the galvanizing furnace and effectively control the zinc liquid temperature according to the heating model.

4.2.6 Combustion system configuration of galvanizing furnace

4.2.6.1 The combustion system shall include low NO_x burners, gas regulating valves, monitoring systems, induced draft fans and temperature sensors, and be equipped with automatic ignition and flame monitoring devices.

4.2.6.2 The burners of the flat flame galvanizing furnace shall be arranged reasonably according to the combustion chamber, the influence of temperature uniformity and the smoke exhaust method.

4.2.6.3 The center line of the burner of the high-speed pulse galvanizing furnace shall be arranged vertically on the center line of the fire channel.

4.2.6.4 The combustion system shall be equipped with a main shut-off valve with alarm

4.3.2 Waste heat system process design

4.3.2.1 When designing the process for collecting and utilizing the waste heat of the production line, energy-saving factors shall be considered, including fully collecting and utilizing the waste heat from production line combustion and workpiece cooling.

4.3.2.2 In the waste heat collection system, the waste heat collection equipment and automatic control system are used to automatically collect or utilize the waste heat from the production line online.

4.3.2.3 The waste heat utilization system uses the collected heat for drying, heating and steam production required by other processes, as well as office life, etc. until the heat energy is fully utilized.

4.3.3 Waste heat collection equipment

4.3.3.1 Waste heat collection equipment shall include heat recovery steam generator, pipelines, control system, accessories and instruments, etc.

4.3.3.2 The design and selection of flue-type heat recovery steam generators shall comply with the requirements of GB/T 28056, YB/T 4483 and JB/T 7603.

4.3.3.3 The design and material selection of pipelines shall comply with the provisions of YB/T 4483. The pipeline surface shall have a thermal insulation layer, and the design of the thermal insulation layer shall comply with the provisions of GB 50126.

4.3.3.4 The design and selection of accessories and instruments for flue-type heat recovery steam generators shall comply with the provisions of YB/T 4483.

4.3.3.5 The thermal efficiency of the heat recovery steam generator shall not be less than 80%.

4.3.4 Waste heat utilization equipment

4.3.4.1 The heat exchange system shall select shell-and-tube polytetrafluoroethylene heat exchangers, stainless-steel coiled pipe heat exchangers or graphite heat exchangers according to the application conditions, and be equipped with waste heat collectors, heat exchangers, pipelines, valve groups and temperature and flow meters.

4.3.4.2 The design and selection of shell-and-tube PTFE heat exchangers shall comply with the requirements of GB/T 27698.3 and HG/T 4172.

4.3.4.3 Stainless-steel Coiled pipe heat exchangers should use pipes specified in GB/T 13296 or GB/T 24593.

4.3.4.4 The design, thermal conductivity and measurement method of graphite heat exchangers shall comply with the requirements of GB/T 8722 and HG/T 3187.

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. <https://www.ChineseStandard.us>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. <https://www.ChineseStandard.net>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies - <https://www.ChineseStandard.us>).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <https://www.chinesestandard.net/AboutUs.aspx>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <https://www.linkedin.com/in/waynezhengwenrui/>

----- The End -----