

Translated English of Chinese Standard: GB/T8749-2021
www.ChineseStandard.net → Buy True-PDF → Auto-delivery.
Sales@ChineseStandard.net

GB

NATIONAL STANDARD OF THE
PEOPLE'S REPUBLIC OF CHINA

ICS 77.140.50

CCS H 46

GB/T 8749-2021

Replacing GB/T 8749-2008

Hot-rolled quality carbon structural steel strip

优质碳素结构钢热轧钢带

Issued on: August 20, 2021

Implemented on: March 01, 2022

Issued by: State Administration for Market Regulation;

**Standardization Administration of the People's Republic of
China.**

Table of Contents

Foreword.....	3
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	7
4 Classification and code	7
5 Order content.....	7
6 Size, shape, weight.....	8
7 Technical requirements	10
8 Test methods.....	13
9 Inspection rules.....	14
10 Packaging, marking and quality certificate	14

Hot-rolled quality carbon structural steel strip

1 Scope

This Standard specifies classification and code, order content, size, shape, weight, technical requirements, test methods, inspection rules and packaging, marking, quality certificate for hot-rolled quality carbon structural steel strip.

This Standard is applicable to hot-rolled quality carbon structural steel strip of which the width is less than 600mm, the thickness is not more than 12mm (hereinafter referred to as the steel strip). The steel strip with a width of 600mm~750mm can refer to this Standard.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

GB/T 222, *Permissible tolerances for chemical composition of steel products*

GB/T 223.5, *Steel and iron - Determination of acid-soluble silicon and total silicon content - Reduced molybdosilicate spectrophotometric method*

GB/T 223.12, *Methods for chemical analysis of iron, steel and alloy. The sodium carbonate separation-diphenyl carbazide photometric method for the determination of chromium content*

GB/T 223.19, *Methods for chemical analysis of iron, steel and alloy - The neocuproine-chloroform extraction photometric method for the determination of copper content*

GB/T 223.23, *Iron, steel and alloy - Determination of nickel content - The dimethylglyoxime spectrophotometric method*

GB/T 223.37, *Iron, steel and alloy - Determination of nitrogen content - Indophenol blue spectrophotometric method after distillation separation*

GB/T 223.59, *Iron, steel and alloy - Determination of phosphorus content - Bismuth phosphomolybdate blue spectrophotometric method and antimony phosphomolybdate blue spectrophotometric method*

GB/T20125, *Low-alloy steel - Determination of multi-element contents - Inductively coupled plasma atomic emission spectrometric method*

GB/T 38813, *General requirements for hot-rolled pickled steel sheet and strip*

3 Terms and definitions

There are no terms and definitions that need to be defined in this Standard.

4 Classification and code

4.1 Classify according to the edge state:

- a) Trimmed steel strip, EC;
- b) Un-trimmed steel strip, EM.

4.2 Classify according to thickness accuracy:

- a) Ordinary thickness accuracy, PT.A;
- b) Higher thickness accuracy, PT.B.

5 Order content

5.1 The order contract or order sheet according to this Standard shall include the following information:

- a) Reference to this Standard;
- b) Specification;
- c) Designation;
- d) Weight;
- e) Edge state (EC or EM);
- f) Delivery state (hot rolled, pickled or other);
- g) Thickness accuracy;
- h) Special requirements.

5.2 If the order contract does not specify the edge state, delivery state, thickness accuracy and other information, then it shall be supplied according to

6.5 Shape

6.5.1 The steel strip shall be delivered in coils. They shall not be loose. The height of one side of the steel strip coil shall not exceed 50mm.

6.5.2 The sickle bend of untrimmed steel strip is not more than 20mm every 5m. The sickle bend of the trimmed steel strip shall not exceed 15mm every 5m.

6.6 Steel strip weight

The steel strip is delivered according to actual weight.

7 Technical requirements

7.1 Steel designation and chemical composition

7.1.1 The steel designation and chemical composition (melting analysis) shall meet the requirements of GB/T 699. Required by the purchaser, agreed by the supplier and the purchaser and indicated in the contract, the requirements for harmful elements sulfur and phosphorus in steel can be tightened.

7.1.2 The allowable deviation of the chemical composition of the finished steel strip shall comply with the relevant regulations of GB/T 222.

7.2 Smelting method

Steel is smelted by converter or electric furnace.

7.3 Delivery state

7.3.1 The steel strip is delivered in hot rolled state. Agreed by the supplier and the purchaser and indicated in the contract, the steel strip with surface pickling can be supplied.

7.3.2 When the steel strip is delivered in the pickled state, it is usually supplied with oil. The applied oil film shall be able to be removed with alkaline solution. Required by the purchaser, agreed by the supplier and the purchaser and indicated in the contract, the surface of the pickled steel strip can also be supplied uncoiled.

7.5.2 For steel strips for cold rolling, the bending test shall be negotiated between the supplier and the purchaser.

7.6 Decarburized layer

Required by the purchaser, the steel strip made of steels of designation 35 and higher carbon content designations can be used to check the depth of surface decarburization. The depth of the single-sided total decarburization layer (full decarburization layer plus partial decarburization layer) shall meet the following requirements:

- a) When the thickness of the steel strip is not more than 3.2mm, the total depth of the decarburization layer is not more than 0.08mm;
- b) When the thickness of the steel strip is greater than 3.2mm, the total depth of the decarburization layer is not more than 2.5% of the actual thickness of the steel strip.

7.7 Surface quality

7.7.1 The surface of the steel strip is not allowed to have bubbles, scars, cracks, folds, inclusions and pressed into the oxide scale, which are harmful to use. The steel strips are not allowed to have visible delamination, and thin scale or rust that hinders inspection of surface defects. Local defects such as scratches, concave surfaces, pits, surface roughness, bumps, whose depth or height does not exceed half of the thickness tolerance, are allowed. The depth or height (calculated from the actual size) is calculated on one side. The minimum thickness allowed by the corresponding specifications of the steel strip shall be ensured.

7.7.2 Untrimmed steel strips are not allowed to have chips, cracks and significant edge waves. Other edge defects whose depth is not more than half of the width tolerance are allowed. The effective width shall ensure the minimum thickness of the steel strip corresponding to the specifications.

7.7.3 The edge of the trimmed steel strip is allowed to have spurs no larger than 0.5mm.

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. <https://www.ChineseStandard.us>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. <https://www.ChineseStandard.net>

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies - <https://www.ChineseStandard.us>).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <https://www.chinesestandard.net/AboutUs.aspx>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <https://www.linkedin.com/in/waynezhengwenrui/>

----- The End -----