Translated English of Chinese Standard: Q/BQB420-2021

<u>www.ChineseStandard.net</u> → Buy True-PDF → Auto-delivery.

<u>Sales@ChineseStandard.net</u>

## **BQB**

# ENTERPRISE STANDARD OF BAOSHAN IRON AND STEEL CO., LTD

Q/BQB 420-2021

Replacing Q/BQB 420-2019

# Hot-Dip Galvanizing/Zinc-Iron Alloy/Zinc-Magnesium Alloy Coated Steel Sheet and Strip

热镀锌锌铁合金锌镁合金镀层钢板及钢带

Issued on: June 04, 2021 Implemented on: August 10, 2021

Issued by: Baoshan Iron and Steel Co., Ltd.

### **Table of Contents**

1 Chemical composition	3
2 Mechanical properties	6
3 Requirements for coating mass	11
4 Requirements for test and inspection	12

### 1 Chemical composition

Table C.1

Designation	Chemical composition (melting analysis) % (mass fraction) no more than						
	С	Si	Mn	P	S	Ti ª	
DC51D+Z, DC51D+ZM, DC51D+ZM2, DC51D+ZF, DD51D+Z	0.18	0.50	1. 20	0.12	0.045	0.30	
DC52D+Z, DC52D+ZM, DC52D+ZM2, DC52D+ZF			0.60	0. 10	0.045	0.30	
DC53D+Z, DC53D+ZM, DC53D+ZM2, DC53D+ZF	1						
DC54D+Z, DC54D+ZM, DC54D+ZM2, DC54D+ZF	0. 12	0.50					
DC56D+Z, DC56D+ZM, DC56D+ZM2, DC56D+ZF							
DC57D+Z, DC57D+ZM, DC57D+ZM2, DC57D+ZF							
<sup>a</sup> Nb is allowed to replace Ti; the total content of Nb and Ti is no more than 0.30% at this time.							

#### Table C.2

Designation	Chemical composition (melting analysis) % (mass fraction) no more than					
Designation	С	Si	Mn	P	S	
S220GD+Z, S220GD+ZM, S220GD+ZM2, S220GD+ZF	0. 25					
S250GD+Z, S250GD+ZM, S250GD+ZM2, S250GD+ZF						
S280GD+Z, S280GD+ZM, S280GD+ZM2, S280GD+ZF		0. 25	0, 60	1. 70	0.10	0, 045
S320GD+Z, S320GD+ZM, S320GD+ZM2, S320GD+ZF			0.00	1.70	0.10	0.045
S350GD+Z, S350GD+ZM, S350GD+ZM2, S350GD+ZF						
S550GD+Z, S550GD+ZM, S550GD+ZM2						

#### Table C.3

	Chemical composition (melting analysis) % (mass fraction)							
Designation	C No more than	Si No more than	Mn No more than	P No more than	S No more than	Alt No less than	Ti <sup>a</sup> No more than	Nb <sup>a</sup> No more than
HC180YD+Z, HC180YD+ZM, HC180YD+ZF	0.01	0.10	0.70	0.06	0.025	0.02	0.12	_
HC220YD+Z, HC220YD+ZM, HC220YD+ZF	0.01	0. 10	0.90	0.08	0.025	0.02	0.12	_
HC260YD+Z, HC260YD+ZM, HC260YD+ZF	0.01	0.10	1.60	0.10	0.025	0.02	0.12	_
HC180BD+Z, HC180BD+ZM, HC180BD+ZF	0.04	0.50	1.00	0.06	0.025	0.02	_	_
HC220BD+Z, HC220BD+ZM, HC220BD+ZF	0.06	0.50	1.00	0.08	0.025	0.02	_	_
HC260BD+Z, HC260BD+ZM, HC260BD+ZF	0.11	0.50	1.00	0.10	0.030	0.02	_	_
HC300BD+Z, HC300BD+ZM, HC300BD+ZF	0.11	0.50	1.00	0.12	0.030	0.02	_	_
HC260LAD+Z, HC260LAD+ZM, HC260LAD+ZF	0. 11	0. 50	0.60	0.025	0.025	0.015	0. 15	0.09
HC300LAD+Z, HC300LAD+ZM, HC300LAD+ZF	0.11	0.50	1.00	0.030	0.025	0.015	0.15	0.09
HC340LAD+Z, HC340LAD+ZM HC340LAD+ZF, HD340LAD+Z	0. 11	0. 50	1.00	0. 030	0. 025	0. 015	0. 15	0.09
HC380LAD+Z, HC380LAD+ZM, HC380LAD+ZF	0. 20	0.50	1.60	0.030	0.025	0.015	0.15	0.09
HC420LAD+Z, HC420LAD+ZM HC420LAD+ZF, HD410LAD+Z	0. 20	0. 50	1.60	0. 030	0. 025	0. 015	0. 15	0.09
HC460LAD+Z, HC460LAD+ZM, HC460LAD+ZF	0. 20	0.50	1.70	0.030	0.025	0.015	0.15	0.09
HC500LAD+Z, HC500LAD+ZM, HC500LAD+ZF	0. 20	0.50	1.70	0.030	0.025	0.015	0. 15	0.09
HC550LAD+Z	0.20	0.50	2.00	0.030	0.025	0.015	0. 15	0.09
HD550LAD+Z	0. 20	0.50	2.00	0.030	0.025	0.015	0. 15	0.09
<sup>a</sup> Ti and Nb can be added individually or in combination. V and B can also be added; and the total content of theses alloy elements is ≤ 0.22%.								

#### This is an excerpt of the PDF (Some pages are marked off intentionally)

#### Full-copy PDF can be purchased from 1 of 2 websites:

#### 1. https://www.ChineseStandard.us

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

#### 2. https://www.ChineseStandard.net

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies https://www.ChineseStandard.us).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): <a href="https://www.chinesestandard.net/AboutUs.aspx">https://www.chinesestandard.net/AboutUs.aspx</a>

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: <a href="https://www.linkedin.com/in/waynezhengwenrui/">https://www.linkedin.com/in/waynezhengwenrui/</a>

----- The End -----