Translated English of Chinese Standard: YBB00212005-2015

www.ChineseStandard.net

Email: Sales@ChineseStandard.net

YBB

National Drugs Packing Containers (Materials) Standards

YBB 00212005-2015

PVC Sheet for Solid Preparation

聚氯乙烯固体药用硬片

YBB 00212005-2015 How to BUY & immediately GET a full-copy of this standard?

- 1. www.ChineseStandard.net;
- 2. Search --> Add to Cart --> Checkout (3-steps);
- 3. No action is required Full-copy of this standard will be automatically & immediately delivered to your EMAIL address in 0~60 minutes.
- 4. Support: Sales@ChineseStandard.net. Wayne, Sales manager

Issued on: August 11, 2015 Implemented on: December 01, 2015

Issued by: China Food and Drug Administration of PRC

PVC Sheet for Solid Preparation

This Standard applies to solid preparation that takes polyvinyl chloride (PVC) resin as main raw material, used for blister packaging of solid pharmaceuticals (tablets, capsules, etc.).

[Appearance] Take an appropriate amount of this product. Place at a bright place under natural light. Visually inspect it. It shall be in uniform color, without bumps, oil stains, foreign material, perforation, impurities. In per 100 cm², the crystal points of 1.3 mm and less than 1.3 mm must not exceed 3. There must be no crystal points over 1.3 mm.

[Identification] (1) IR* Take an appropriate amount of this product; determine according to the Fourth Method of Packaging materials - Infrared spectroscopy (YBB 00262004-2015) and it shall be consistent with the control map.

(2) **Density** Take about 2 g of this product. Determine according to Density measurement method (YBB 00132003-2015) and it shall be $1.35 \sim 1.45 \text{ g/cm}^3$.

[Physical performance] Water vapor permeation Take an appropriate amount of this product. Determine according to the First Method test conditions of Water vapor transmission measurement method (YBB 00092003-2015) or the Second Method (test temperature of 23°C \pm 0.5°C, relative humidity of 90% \pm 2%) or the Fourth Method (test temperature of 23°C \pm 0.5°C, relative humidity of 90% \pm 2%). It must not exceed 2.5 g/(m² • 24h).

Oxygen permeation Take an appropriate amount of this product. Determine according to the First Method of Gas permeation measurement method (YBB 00082003-2015). It must not exceed 30 cm^3 / ($\text{m}^2 \cdot 24 \text{ h} \cdot 0.1 \text{ MPa}$).

Tensile strength Take an appropriate amount of this product. Determine according to Tensile performance measurement method (YBB 00112003-2015). Test speed (without load) is 100 mm/min ± 10 mm/min. Sample is Type I. The average of longitudinal, transverse tensile strength must not be less than 44 MPa.

Impact resistance Take an appropriate amount of this product. Extract 150mm x 50mm test piece, 5 pieces in total vertically and horizontally. Place the sample at a temperature of 23° C \pm 2° C and relative humidity of $50\% \pm 5\%$ for over 4 hours. Carry out the test under the above conditions. Fix the sample on the falling ball impact testing machine of which the span is 100 mm. Select the steel ball and drop height according to Table 1 to make the ball free fall in the central part of the span. It is not allowed to have more than two pieces of damage at the vertical and horizontal directions.

Table 1 -- Selection of steel ball and drop height

mm

Sample thickness	Drop height	Steel ball diameter
0.20 ~ 0.30	600	25 (60 g ± 6 g)
0.31 ~ 0.40	600	28.6 (100 g ± 10 g)

This is an excerpt of the PDF (Some pages are marked off intentionally)

Full-copy PDF can be purchased from 1 of 2 websites:

1. https://www.ChineseStandard.us

- SEARCH the standard ID, such as GB 4943.1-2022.
- Select your country (currency), for example: USA (USD); Germany (Euro).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Tax invoice can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with download links).

2. https://www.ChineseStandard.net

- SEARCH the standard ID, such as GB 4943.1-2022.
- Add to cart. Only accept USD (other currencies https://www.ChineseStandard.us).
- Full-copy of PDF (text-editable, true-PDF) can be downloaded in 9 seconds.
- Receiving emails in 9 seconds (with PDFs attached, invoice and download links).

Translated by: Field Test Asia Pte. Ltd. (Incorporated & taxed in Singapore. Tax ID: 201302277C)

About Us (Goodwill, Policies, Fair Trading...): https://www.chinesestandard.net/AboutUs.aspx

Contact: Wayne Zheng, Sales@ChineseStandard.net

Linkin: https://www.linkedin.com/in/waynezhengwenrui/

----- The End -----